

## JEDYNKA® GRUNT

### PRIMER FOR WALLS AND CEILINGS



Improves topcoat adhesion  
Reduces substrate absorbancy  
Allows walls to „breath”  
Great coverage: approx. 10 m<sup>2</sup>/l per one coat

#### PRODUCT DESCRIPTION

White waterborne primer. Reduces substrate absorbancy, improves topcoat adhesion and increases coverage of waterborne dispersion, latex, acrylic paints etc.

#### RECOMMENDED USES

For priming interior walls and ceilings, offices and public area, included school facilities and commercial buildings and production premises. It can be applied on plaster, concrete, gypsum, chipboard, drywalls, and for renovation of previously painted surfaces.

#### APPLICATION

##### Painting

All painted surfaces must be dry, the air temperature must not be lower than +5°C and the relative humidity below 80%. Before painting, the paint should be thoroughly mixed and, if necessary, diluted with max. 5% water. Apply one coat of Jedynka Grunt with a brush, roller or by spraying.

#### CLEANING OF EQUIPMENT

Wipe away excessive paint from the tools before cleaning. Thinner/tools cleaning: water.

#### COLORS

White

#### GLOSS

Full matt

#### COVERAGE

Up to 10 m<sup>2</sup>/l with one coat of paint. Performance is largely dependent on factors such as absorption, surface texture and application method.

#### CAN SIZES

3,0 L, 10,0 L

#### HEALTH AND SAFETY

After application the room must be ventilated till all paint odour disappears, after that the room is ready to use. Do not pour liquid waste into drains. Empty cans as well as cans with liquid waste should be taken to a disposal according to the local regulations. For more information please contact local authority. Safety data sheet available on request. Warning! Hazardous respirable droplets may be formed when sprayed. Do not breathe spray or mist. Contains 1,2-benzisothiazol-3(2H)-one (BIT) and reaction mass of 5-chloro-2-methyl-2H-isothiazol-3-one and 2-methyl-2H-isothiazol-3-one (3:1) (C(M)IT/MIT (3:1)). May produce an allergic reaction. Wear protective gloves. This product contains a biocidal product for the preservation of the product during storage. Contains: 1,2-benzisothiazol-3(2H)-one (BIT) and reaction mass of 5-chloro-2-methyl-2H-isothiazol-3-one and 2-methyl-2H-isothiazol-3-one (3:1) (C(M)IT/MIT (3:1)). Protect from frost

#### STORAGE AND TRANSPORTATION

Protect from frost and sunlight. Transport and storage in tightly closed containers in temperatures from +5°C to +25°C.

## TECHNICAL DATA

Weight solid (%)	Min. 50%
Viscosity (+23°C) KU	100-110
Density (kg/l)	max. 1,5
Drying times	At +23°C, at 50% relative humidity, the paint dries for approx. 1 hour. The best way to paint the topcoat is to do it after a minimum of 2 hours.

## ADDITIONAL INFORMATION

Cat. A/a. Acceptable VOC content since 2010 - 30 g/l. Product contains below: 30 g/l VOC.